

BLACKFRIAR PAINTS LTD

TECHNICAL DATA SHEET

Revision
date:
16/03/07

BF074 Blackfriar Terebine Liquid Driers.

<u>Product Information</u>	<u>Technical Spec Composition</u>	<u>Recommended Spreading Rate</u>
N.B. Read container instructions prior to use	Cobalt and zirconium carboxylate in white spirit and naptha.	Not applicable.
<u>Description</u>	<u>Properties</u>	<u>Thinning</u>
A solvent-based solution of liquid metallic driers.	VOC Content: 750 gm/litre.	Do not thin.
<u>Usage/purpose</u>	<u>Performance</u>	<u>Drying Time</u>
Use to speed up the drying of most solvent based paints and varnishes under poor drying conditions.	Formulated to speed up drying in adverse conditions.	Drying time of paint or varnish will be reduced. See also under limitations.
<u>Characteristics</u>	<u>Surface Preparation</u>	<u>Cleaning</u>
A purple liquid with a strong solvent odour.	Not applicable.	Clean application equipment or spills with white spirit.
<u>Finish</u>	<u>Application Method</u>	<u>Limitations</u>
Not a finish	Ensure product is thoroughly mixed before use. Add <u>up to</u> 56 mls per 5 litres of solvent based paint or varnish, (see also under limitations). Stir in thoroughly before using paint.	Blackfriar Driers are not suitable for use in water based paints, cellulose or non-convertible (e.g Pliolite masonry) finishes. Excessive additions of driers may cause the paint film to shrivel or lead to early failure.
<u>Colour(s)</u>	For Technical Enquiries and Material Safety Data sheets Telephone 0191 4106611	<u>Environmental Info.</u>
<u>Packaging</u>		Solvent based. Do not empty into drains or watercourses.
125, 250, 500ml and 1 litre.		Tor Coatings Ltd. Portobello Industrial Est, Birtley Chester-le Street County Durham DH3 2RE
<u>Disclaimer;</u> The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. It is our recommendation that a trial area is first coated to ensure the product is satisfactory to individual requirements.		